

# Turned parts

## Alliages et normes

WROUGHT COPPER ALLOYS				
ISO	European Standard	UNS	Lba	Comments
UNLEADED BRASSES (Cu-Zn) (C20000 to C29999)				
CuZn40	CW509L	C28000	EnviB10	26% IACS, 70% machinability rating
CuZn40Al	CW509L	C28000	EnviB1	26% IACS, 60% machinability rating
LEADED BRASSES (Cu-Zn-Pb) (C30000 to C39999)				
CuZn35Pb2	CW601N	C34200 C34500 C35300	63 N	23% IACS, 80% machinability rating
CuZn36Pb3	CW603N	C36000	61 A	25% IACS, 100% machinability rating
CuZn38Pb2	CW608N	C35300	60 A	22% IACS, 80% machinability rating
CuZn38Pb2	CW608N	C37700	60 M	22% IACS, 80% machinability rating
CuZn39Pb0,5	CW610N	C36500	60 S	24% IACS, 55% machinability rating
CuZn39Pb3	CW614N	C38500	58 D	25% IACS, 100% machinability rating